



**CHEMICAL FOR ELECTRONICS SINCE 1982**

Address 21050 GORLA MAGGIORE (VA) - Via Boschi Belli, 6 - Italy - Phone +39 0331.36871

## TECHNICAL INFORMATION

# PEEL OUT 4200 CHEM

### DESCRIPTION

PEEL OUT 4200 is an aqueous resin opportunely modified to ensure temporary protection from soldering of printed circuit boards.

### METHODS OF APPLICATION

Easy to use.  
Apply the PEEL OUT 4200 on the area to protect with a dispenser or with a brush. Place a layer of approx. 1-2 mm.  
Before welding, the product must be dry

### METHODS OF DRYING

At ambient temperature the drying time is approximately 3 - 4 h, in the oven at 80 ° C is about 1-4 minutes. The product is provided at the right density and viscosity for use. For special applications can be diluted with demineralized water. After welding the PEEL OUT 4200 is removed with a slight manual pressure. PEEL OUT contains no silicone and oils. It leaves no residue on protected areas, does not pollute the solder.

### PACKAGING

The PEEL OUT 4200 is available in tanks of 5 Kg.